

MUNKEN POLAR ROUGH

Extraordinary printing demands extraordinary design paper. The uncoated, extra tactile surface of Munken Polar Rough and its crisp white shade make a perfect combination for well-defined images and even more of a natural paper feel. Thanks to high bulk you can choose a lower grammage and keep thickness as well as paper stability for the best final result. Munken Polar Rough is developed for offset print and also suitable for

various kinds of printing techniques; flexo, laser, xerography, digital printing, inkjet and for preprint applications. Also available is a natural white, Munken Lynx Rough, a cream shaded version, Munken Pure Rough and the highwhite Munken Kristall Rough. Munken Polar Rough standard products are available as EU Ecolabel, FSC® FSC-C020637 and PEFC™ PEFC/05-33-99 certified.



The mark of responsible forestry



BASIC INFORMATION

Optimized for colour printing.
Available in sheets. Available in reels

ENVIRONMENT / SAFETY

EU Ecolabel, ECF, ISO 14001, EMAS, Paper Profile, Safety of Toys, Food contact, Age resistant (ISO 9706), Woodfree, FSC_C020637, The paper is inspected for Nordic Ecolabelled printing, PEFC_053399

PRINTING TECHNIQUES

Offset, Flexo, Laser, Inkjet
(black/white)

SHADE

Crisp White

SURFACE

Uncoated, Rough

MUNKEN POLAR ROUGH

| Grammage (g/m ²) | 90 | 100 | 120 | 150 | 170 | 300 ^B |
|------------------------------|-----|-----|-----|-----|-----|------------------|
| Opacity (%) | 91 | 93 | 95 | 97 | 98 | 100 |
| Thickness (µm) | 126 | 140 | 168 | 210 | 238 | 420 |
| Bulk (thickness/grammage) | 1.4 | 1.4 | 1.4 | 1.4 | 1.4 | 1.4 |
| Whiteness (CIE) | 145 | 145 | 145 | 145 | 145 | 145 |
| Brightness (ISO 2470/D65 %) | 109 | 109 | 109 | 109 | 109 | 109 |
| Roughness (Bendtsen, ml/min) | 550 | 550 | 550 | 550 | 550 | 550 |

Screen recommended 133-150 lpi

^B Laminated paper

Values are targets only and can be subject to changes over time without prior notice. You will find the latest technical information and other technical recommendations about our products at arcticpaper.com