

## Magno Natural **Product Information**



Magno Natural is an uncoated fine paper available in sheets and reels for offset printing

## **Technical specifications**

Parameter	Standard	Unit												
Basis weight	ISO 536	g/m²	70	80	90	100	110	120	140	150	170	190	250	300
CIE whiteness (D65/10°)	ISO 11475	%	144	144	144	144	144	144	144	144	144	144	144	144
Opacity	ISO 2471	%	90	91,5	93	94,5	95,5	96,5	98	98,5	>99	>99	>99	>99
Bulk	ISO 534	cm³/g	1.27	1,27	1,25	1,24	1,24	1,20	1,20	1,20	1,17	1,17	1,17	1,15

## Mill Certification



The quality of the manufacturing is managed according to the requirements of ISO 9001.



The environmental aspects of the mill are managed according to the requirements of ISO 14001.



The energy consumed and the emissions generated by the mill are managed according to ISO 50001.



The mills are both FSC and PEFC CoC certified, and all wood raw material originates from sustainable and controlled sources.



The mills are both FSC and PEFC CoC certified, and all wood raw material originates from sustainable and controlled sources.



The health and safety of the mill employees are managed according to the requirements of OHSAS 18001.

## Product Certification

with dry and fatty foodstuff.



Only approved chemicals used, in compliance with BfR recommendation XXXVI



Meets the purity requirements (heavy metal content) of EN 71-3 'Toy Safety', part 3 'Migration of certain elements' and part 9 'Organic chemical compounds'.

'Paper and Board for Food Contact'. Magno Natural is suitable for direct contact



The key environmental parameters of the product are presented at the Paper Profile.

PEFC<sup>™</sup> certification on request/subject to availability.



Archivability tested according to the requirements of DIN 6738, Lifespan class - LDK 24-85.

ECF Pulp is bleached without the use of elemental chlorine (ECF).



Dry toner: Suitable for dry toner.

Packaging of product complies with packaging and waste directive 94/62/EC (article 11). Magno Natural is fully recyclable.